

Raybo Chemical Company

TELEPHONE: 304-525-5171

RAYBO 6 AntiSag Improve Dispersion Control Sag Stop Settling					
E F G	EATURES	SYSTEM	COMMENTS	USAGE (%)	R
	trols Sagging attling	Solvent	Non-Puffing	0.3 - 3% of Total Weight	E F E R E N C E
PERFORMANCE The superior wetting properties of RAYBO 6 make it well suited for use in a wide range of products. It exhibits a range of system compatibility not shared with other materials used for sag control. Puffing agents generally used for sag control can produce viscosity increases in the paint system. RAYBO 6 produces sag and settling control by improved wetting and dispersion rather than by viscosity increase, even with post addition. In controlling settling, RAYBO 6 will not produce side effects such as loss of adhesion, film					
		reduced gloss associate	ed with the use of anti-se		
When used as a dispersant, the high wetting capability of RAYBO difficult to wet pigments such as carbon black and phthalocyanine dispersing puffy pastes. In high solids systems using high shear for produce increased color intensity, fineness of dispersion and decr					very effective in AYBO 6 will
ADVANTAGES	 Convenient liquid added at any stage of manufacture for sag and settling control High System compatibility Dispersant plus sag and settling control Excellent suspension agent for metallic pigments 				
RECOMMENDATIONS	 For Sag Control – 1 – 3% of total paint For Settling Control – 0.3 – 1% of total paint For Dispersion – 0.5 – 5% of pigment weight Compatible with most solvent systems, RAYBO 6 is not recommended for epoxies or 2 part urethane systems. For sag and settling control, add at any stage of manufacture 				
PHYSICAL DATA**	Gardner ViscosityB - C Weight/Gallon7.4 lbs Active100%				
CONTAINER SIZES	North Americ Global Zones	a: 5 gal. pail*, 55 gal. d : 5 gal. pail*, 55 gal. : ** Troine Brancetier and	drum.		20100104

* One gallon containers available upon request.

** Typical Properties; not sales specifications.

The information and date stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty either expressed or implied, is made or intended. Use by customer should be based upon its own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.



Performance Additives Department Huntington, WV 25721 Tel: 304-525-5171 Fax: 304-525-2921 U.S. Marketing Division Raybo Chemical Company Huntington, WV 25721 Tel: 304-525-5172 Fax: 304-525-2921



Exclusive Export Management Company W.R. Magnus, Inc. Tel.: 301-263-6124 Email: rwmagnus@cocexport.com



Global Dist Zones:

Representatives in 31 Countries